

Schuller Eh'klar GmbH
AUSTRIA
 Im Astenfeld 6
 A – 4490 St. Florian
 Tel.(0043) 07224/68 200
 Fax(0043) 07224/68 282
 E-Mail: office@schuller.eu
 www.schuller.eu



St. Florian, 07.01.2014

PAPER COVERING

(Articlenumbers: 45951, 45952, 45953, 45956)

Description:

This paper covering is a machine glazed kraft paper, distinguished by its high strength and excellent surface properties of the glazed side. A very good dimensional stability, high stiffness and excellent runnability are features of this paper quality.

Technical data:

Material	Advantage MG Kraft is made of pure unbleached long-fibre sulphate pulp	
Basis weight	40 g/m ²	ISO 536
Tensile strenght	MD 4,16 kN/m CD 1,96 kN/m	ISO 1924-3
Stretch at break	MD 1,8 % CD 2,1 %	ISO 1924-3
Tear Index	MD 7,0 mN.m ² /g CD 9,0 mN.m ² /g	ISO 1974
Bursting Strenght	170 kPa	ISO2758
Air resistance	9 sec.	ISO 5636-5
Cobb-60“	27 g/m ²	ISO 535
Roughness	RS 190 ml/min MG 800 ml/min.	ISO 8791-2

MD ... Machine direction

RS ... Reverse side

CD ... Cross direction

MG ... Machine glazed side

Approvals & Certifications:

- The paper fulfils the German, Dutch, CONEG and FDA regulations for papers in contact with foodstuffs.
- The production is certified according to the quality management system ISO 9001 and the environmental management system ISO 14001.

Application:

- Suitable for all kinds of covering jobs
- Perfect in combination with the most masking tapes

Storage:

Storage at room temperature (between 10 ° C and +30 ° C at a relative humidity of 50%). Keep away from direct sunlight and other heat sources.